

**Sumika Polycarbonate Limited**

Technical Service & Development Lab
1-98 Kasugade Naka 3-Chome
Konohana-Ku, Osaka 554-8558 Japan

File Number: E123529

CR3241

Polycarbonate/Polyester (PC/PER), pellets



Flammability	Value	Test Method
Flame Rating		
0.75 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
0.75 mm, ALL	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec		UL 746B
0.75 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Imp		UL 746B
0.75 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Str		UL 746B
0.75 mm	50.0 °C	
3.0 mm	50.0 °C	