

**Sumika Polycarbonate Limited**

Technical Service & Development Lab
1-98 Kasugade Naka 3-Chome
Konohana-Ku, Osaka 554-8558 Japan

File Number: E123529

TR(bb)1A

Polycarbonate (PC), pellets

(bb) - Followed by suffix numbers 090 - 180 incl. denoting melt flow rate.



Flammability	Value	Test Method
Flame Rating		UL 94
0.35 mm, CL	V-2	IEC 60695-11-10, -20
3.0 mm, CL	V-2	
Thermal	Value	Test Method
RTI Elec		UL 746B
0.35 mm	80.0 °C	
3.0 mm	80.0 °C	
RTI Imp		UL 746B
0.35 mm	80.0 °C	
3.0 mm	80.0 °C	
RTI Str		UL 746B
0.35 mm	80.0 °C	
3.0 mm	80.0 °C	